

Silicone transfer tubing



Silicone transfer tubing

Features and benefits

- Safe, reliable and value-based general purpose fluid transfer solution
- Manufactured and packed in an ISO 14644-1 Class 7 cleanroom
- Comprehensive stock of a wide range of sizes
- Validation pack, including extractable profiles and USP <85> Bacterial Endotoxin testing
- Autoclavable to 121 °C and gamma stable up to 50 kGy



Technical specifications

	Silicone transfer tubing
Bore size	3.2 - 25.4 mm
Bore size	0.125 - 1 in
External diameter	6.4 - 38.1 mm
External diameter	0.25 - 1.5 in
Length	7.6 - 30 m
Length	25 - 100 Ft
Transparency	Translucent
Certification	ADCF, ISO 10993, ISO Class 7, Ph. Eur. 3.1.9, TOC, USP Class VI
Operating temperature range	-65 °C to 254 °C
Operating temperature range	-85 °F to 490 °F
Hardness, shore A (5sec)	50
Specific gravity	1.14 g/cm ³
UV resistance	High
Burst pressure	1.9 - 8.3 bar
Burst pressure	27 - 120 psi
Ultimate tensile strength	8.3 MPa
Ultimate tensile strength	1200 psi
Max. operating pressure	2.8 bar
Max. operating pressure	40 psi
Elongation at break	400 %
Shelf life	5 years
Gamma stability	25 kGy to 50 kGy
Autoclave stability	121 °C 30 minutes

ASTM methods Hardness: ASTM D 2240; Specific gravity: ASTM D 792; Tear B, Ultimate tensile strength,; Elongation at break, Tensile stress at 100% elongation; ASTM D 412

Max operating pressure is dependent on tube size

Materials of construction

	Silicone transfer tubing
Material	Platinum-cured silicone

Product codes

I.D.	O.D.	Coil size		
		30 m (100 ft)	15 m (50 ft)	7.6 m (25 ft)
3.2 (0.125)	6.4 (0.250)	BPS-0125-0250-100	BPS-0125-0250-50	—
3.2 (0.125)	8.0 (0.312)	BPS-0125-0312-100	BPS-0125-0312-50	—
3.2 (0.125)	9.6 (0.375)	BPS-0125-0375-100	BPS-0125-0375-50	—
4.8 (0.187)	8.0 (0.312)	BPS-0187-0312-100	BPS-0187-0312-50	—
4.8 (0.187)	9.6 (0.375)	BPS-0187-0375-100	BPS-0187-0375-50	—
4.8 (0.187)	11.2 (0.437)	BPS-0187-0437-100	BPS-0187-0437-50	—
6.4 (0.250)	9.6 (0.375)	BPS-0250-0375-100	BPS-0250-0375-50	—
6.4 (0.250)	11.2 (0.437)	BPS-0250-0437-100	BPS-0250-0437-50	—
6.4 (0.250)	12.7 (0.500)	BPS-0250-0500-100	BPS-0250-0500-50	—
8.0 (0.312)	11.2 (0.437)	BPS-0312-0437-100	BPS-0312-0437-50	—
8.0 (0.312)	12.7 (0.500)	BPS-0312-0500-100	BPS-0312-0500-50	—
8.0 (0.312)	14.3 (0.562)	BPS-0312-0562-100	BPS-0312-0562-50	—
9.6 (0.375)	12.7 (0.500)	BPS-0375-0500-100	BPS-0375-0500-50	—
9.6 (0.375)	14.3 (0.562)	BPS-0375-0562-100	BPS-0375-0562-50	—
9.6 (0.375)	15.9 (0.625)	BPS-0375-0625-100	BPS-0375-0625-50	—
12.7 (0.500)	15.9 (0.625)	—	BPS-0500-0625-50	BPS-0500-0625-25
12.7 (0.500)	17.5 (0.687)	—	BPS-0500-0687-50	BPS-0500-0687-25
12.7 (0.500)	19.0 (0.750)	—	BPS-0500-0750-50	BPS-0500-0750-25
15.9 (0.625)	22.2 (0.875)	—	BPS-0625-0875-50	BPS-0625-0875-25
15.9 (0.625)	25.4 (1.000)	—	BPS-0625-1000-50	BPS-0625-1000-25
19.0 (0.750)	25.4 (1.000)	—	BPS-0750-1000-50	BPS-0750-1000-25
19.0 (0.750)	28.6 (1.125)	—	BPS-0750-1125-50	BPS-0750-1125-25
25.4 (1.000)	31.2 (1.250)	—	BPS-1000-1250-50	BPS-1000-1250-25
25.4 (1.000)	34.9 (1.375)	—	BPS-1000-1375-50	BPS-1000-1375-25
25.4 (1.000)	38.1 (1.500)	—	BPS-1000-1500-50	BPS-1000-1500-25

Disclaimer: The information contained in this document is believed to be correct but Watson-Marlow Limited accepts no liability for any errors it contains and reserves the right to alter specifications without notice. It is the user's responsibility to ensure product suitability for use within their application. Watson-Marlow and WMArchitect are registered trademarks of Watson-Marlow Limited. BioClamp, BioBarb, FlatBioEndCap, BioEndCap, BioValve and BioTube applicator are Trademarks of BioPure Technology Limited. Tri-Clamp is a registered trademark of Alfa Laval Corporate AB. Q-Clamp is used under licence.

wmfts.com/global



01 May 2024